

Mold Max® 30

Silicone
Smooth-On, Inc

Message:

Mold Max® Silicones are tin-cured silicone rubber compounds that have exceptional working properties and library life. Mold Max® Silicones feature Smooth-On's exclusive "Libra®" catalyst for long library life. Mold Max® silicones can be pigmented with Silc Pig® silicone colorants. Pot life for the pourable silicones is 45 minutes and they cure overnight at room temperature.

Mold Max® Silicones will reproduce the finest detail and are suitable for a variety of industrial and art related applications including making molds for reproducing prototypes, furniture, sculpture and architectural elements. Mold Max® 10, 20, 25 and 30 silicones can be thickened with THI-VEX® additive for brush-on applications. (Note: THI-VEX® is NOT compatible with Mold Max® 40 or 60). Mold Max® 60 offers highest heat resistance for casting metal (see separate technical bulletin).

Mold Max® Silicones can be used to cast a variety of materials including wax, gypsum, low melt alloys/metals and urethane, epoxy or polyester resins (without using a release agent).

General Information			
Uses	Modeling Material		
	Prototyping		
Appearance	Pink		
Processing Method	Casting		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm³	ASTM D1475
Specific Volume	0.849	cm³/g	ASTM D1475
Mixing Ratio	100A:10B by weight		
Operating Temperature	-54 to 204	°C	
Molding Shrinkage - Flow	0.20	%	ASTM D2566
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	30		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	0.758	MPa	ASTM D412
Tensile Strength (Break)	3.98	MPa	ASTM D412
Tensile Elongation (Break)	300	%	ASTM D412
Tear Strength ¹	21.9	kN/m	ASTM D624
Thermoset	Nominal Value	Unit	Test Method
Pot Life	45	min	
Thermoset Mix Viscosity	25000	cP	ASTM D2393
Demold Time	1400	min	
NOTE			
1.	Die B		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

