CENUSIL® R 160

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, HTV Sealant Profiles, Construction

General Information				
Features	General Purpose			
	Low Compression Set			
Uses	Automotive Applications			
	Compounding			
Processing Method	Compression Molding			
	Press Molding			
Uncured Properties	Nominal Value	Unit	Test Method	
Color	Translucent			

Uncured Properties	Nominal Value	Unit	Test Method
Color	Translucent		
Density	1.17	g/cm³	DIN 51757
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	60		DIN 53505
Tensile Strength	9.00	МРа	DIN 53504
Tensile Elongation at Break	310	%	DIN 53504
Compression Set	10	%	DIN ISO 815-B
Tear Strength	17.0	kN/m	ASTM D624B
Rebound Resilience	55	%	DIN 53512

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

