

# Borealis PE MG7547S

High Density Polyethylene

Borealis AG

## Message:

MG7547S is a high-density polyethylene produced by a low pressure process. This grade has an excellent impact strength and low distortion even at low temperatures. It also contains UV-stabilizer, which makes this grade especially suited for outdoor applications.

General Information			
Additive	UV stabilizer		
Features	Low warpage		
	Impact resistance, good		
	Good UV resistance		
	Good liquidity		
	Good toughness		
Uses	Waste container		
	Container		
	Outdoor application		
	Loading box		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.954	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.0	g/10 min	ISO 1133
Molding Shrinkage	1.0 - 2.0	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	61		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Injection Molded)	950	MPa	ISO 527-2/1
Tensile Stress (Yield, Injection Molded)	24.0	MPa	ISO 527-2/50
Tensile Strain (Yield, Injection Molded)	10	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	7.0	kJ/m <sup>2</sup>	ISO 179/1eA
23°C	11	kJ/m <sup>2</sup>	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature <sup>1</sup> (0.45 MPa, Unannealed)	71.0	°C	ISO 75-2/B
Injection	Nominal Value	Unit	

Processing (Melt) Temp	210 - 275	°C
Mold Temperature	10.0 - 40.0	°C
Injection Rate	Fast	
Injection instructions		
Holding pressure: As low as possible		
NOTE		
1.	Injection molded specimen	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT