Moplen HP525J

Polypropylene Homopolymer

PolyMirae

Message:

Moplen HP525J is a Polypropylene Homopolymer (PP Homopolymer) material. It is available in Asia Pacific.

Important attributes of Moplen HP525J are:

Food Contact Acceptable

Good Aesthetics

Good Processability

High Stiffness

High Strength

Typical applications include:

Film

Food Contact Applications

General Information					
Features	Barrier Resin				
	Food Contact Acceptable				
	General Purpose				
	Good Processability				
	Good Stretchability				
	High Stiffness				
	High Strength				
	Homopolymer				
	Opticals				
Uses	Bi-axially Oriented Film				
	General Purpose				
Agency Ratings	FDA 21 CFR 177.1520				
Forms	Pellets				
Physical	Nominal Value	Unit	Test Method		
Density	0.900	g/cm³	ASTM D1505		
Melt Mass-Flow Rate (MFR) (230°C/2.16					
kg)	3.0	g/10 min	ASTM D1238		
Hardness	Nominal Value	Unit	Test Method		
Rockwell Hardness (R-Scale)	98		ASTM D785		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Yield, Injection Molded)	34.3	MPa	ASTM D638		
Tensile Elongation (Yield, Injection Molded)	12	%	ASTM D638		
Flexural Modulus (Injection Molded)	1520	MPa	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
mpaot	TOTHING VOICE	O.n.	Tool Would		

Notched Izod Impact (23°C, Injection					
Molded)	39	J/m	ASTM D256		
Thermal	Nominal Value	Unit	Test Method		
Deflection Temperature Under Load (0.45	;				
MPa, Unannealed, Injection Molded)	105	°C	ASTM D648		
Vicat Softening Temperature	153	°C	ASTM D1525		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

