

TOTAL Polypropylene PPR 6298

Polypropylene Random Copolymer

TOTAL Refining & Chemicals

Message:

Total Petrochemicals PPR6298 S01 is a random copolymer polypropylene with a Melt Flow Index of 8 g/min for the cast extrusion of films with excellent heat weldability and optical properties.

Polypropylene PPR6298 S01 is formulated with slip and anti-block agents. It is intended for food, magazine or textile packaging, for lamination films... as well as for stationary supplies.

General Information			
Additive	Antiblock (1890 ppm)		
	Slip (1890 ppm)		
Features	Antiblocking		
	Food Contact Acceptable		
	Opticals		
	Random Copolymer		
	Slip		
	Weldable		
Uses	Film		
	Food Packaging		
	Packaging		
	Stationary Supplies		
Agency Ratings	EC 1907/2006 (REACH)		
Forms	Pellets		
Processing Method	Cast Film		
Physical	Nominal Value	Unit	Test Method
Density	0.902	g/cm ³	ISO 1183
Apparent Density	0.53	g/cm ³	ISO 60
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	850	MPa	ISO 178
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	140	°C	ISO 3146

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

