

# Beetafin® L9015

Polyurethane (Polyester based)

BIP (Oldbury) Limited

## Message:

An anionic, medium hardness, flexible, light fast polyester based, aliphatic aqueous polyurethane dispersion.

Characteristics:

Gives hard but flexible films

Higher viscosity for adhesive applications

Gives high clarity films that do not discolour on exposure to daylight

Activation temperature approximately 90°C

Good adhesion to synthetic and natural materials

Applications:

Leather Finishing

Adhesives

Textile Coatings

Hot melt adhesives

Textile Finishing

Pigment binders

General Information			
Features	Aliphatic		
	Good Adhesion		
	Good Flexibility		
	High Clarity		
	Medium Hardness		
Uses	Adhesives		
	Coating Applications		
	Textile Applications		
Physical	Nominal Value	Unit	
pH	8.0		
Solids Content	35	%	
Films	Nominal Value	Unit	
Tensile Modulus - 100%	25.0	MPa	
Tensile Strength - MD (Break)	50.0	MPa	
Tensile Elongation - MD (Break)	400	%	
Uncured Properties	Nominal Value	Unit	Test Method
Viscosity (25°C)	1.5	Pa · s	Brookfield

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

