

MBA PP 2131 (China)

Polypropylene Copolymer

MBA Polymers

Message:

A post-consumer recycled polypropylene copolymer for general use. Available in standard grey (reference 70/15) and standard black (reference 90/04). Other colors may be available upon request.

General Information	
Recycled Content	Yes
Features	Copolymer
Uses	General Purpose
Appearance	Black
	Colors Available
	Grey
Forms	Pellets
Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	23.0	MPa	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	5.0	kJ/m ²	ISO 180/1A
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	1.0 to 2.0	hr	
Suggested Max Moisture	0.050 to 0.10	%	
Processing (Melt) Temp	190 to 220	°C	
Mold Temperature	30.0 to 60.0	°C	
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	1.0 to 2.0	hr	
Suggested Max Moisture	0.050 to 0.10	%	
Melt Temperature	180 to 210	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT