

Grivory® GVX-7 H black 9915

Polyamide 66 + PA 6I/X

EMS-GRIVORY

Message:

Grivory® GVX-7 H black 9915 is a Polyamide 66 + PA 6I/X (Nylon 66+Nylon 6I/X) material filled with 70% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for extrusion or injection molding.

Important attributes of Grivory® GVX-7 H black 9915 are:

Flame Rated

RoHS Compliant

Good Mold Release

Heat Stabilizer

Typical applications include:

Automotive

Electrical/Electronic Applications

Appliances

Consumer Goods

Engineering/Industrial Parts

General Information		
UL YellowCard	E53898-100966891	E53898-100966892
Filler / Reinforcement	Glass Fiber,70% Filler by Weight	
Additive	Heat Stabilizer	
Features	Aromatic	
	Good Flow	
	Good Mold Release	
	Heat Stabilized	
Uses	Appliance Components	
	Automotive Applications	
	Automotive Exterior Parts	
	Automotive Interior Parts	
	Connectors	
	Consumer Applications	
	Electrical/Electronic Applications	
	Engineering Parts	
	Household Goods	
	Hydraulic Applications	
	Industrial Applications	
	Pneumatic Applications	
	Power/Other Tools	
	Sporting Goods	
RoHS Compliance	RoHS Compliant	
Appearance	Black	

Forms	Granules			
Processing Method	Extrusion Injection Molding			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.85	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.20	--	%	
Flow	0.10	--	%	
Water Absorption				ISO 62
Saturation, 23°C	2.9	--	%	
Equilibrium, 23°C, 50% RH	1.0	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	370	360	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	28000	27500	MPa	ISO 527-2
Tensile Stress (Break)	290	260	MPa	ISO 527-2
Tensile Strain (Break)	1.5	1.5	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	15	15	kJ/m ²	
23°C	15	15	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	60	60	kJ/m ²	
23°C	60	60	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
1.8 MPa, Unannealed	250	--	°C	ISO 75-2/A
8.0 MPa, Unannealed	220	--	°C	ISO 75-2/C
Continuous Use Temperature				Internal Method
-- ¹	100 to 120	--	°C	
-- ²	220	--	°C	
Melting Temperature ³	260	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.0E-5	--	cm/cm/°C	
Transverse	3.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+12	1.0E+12	ohms · cm	IEC 60093

Electric Strength	33	33	kV/mm	IEC 60243-1
Comparative Tracking Index	--	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	HB	--		IEC 60695-11-10, -20
Additional Information	Dry	Conditioned		Test Method
ISO Type	PA66+PA6I/X, MH, 14-250, GF70			ISO 1874
NOTE				
1.	Long Term			
2.	Short Term			
3.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT