En Chuan 6120TA-ISO

Thermoset Polyester

En Chuan Chemical Industries Co,. Ltd.

Message:

This is a ISOphthalic type resin. It contains accelerator and thixotropy. 6120TA-ISO is designed for special products that require high resistance in chemical, weathering, and heat distortion.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	m-benzene dimethyl		
	Good chemical resistance		
	Good weather resistance		
Hardness	Nominal Value		Test Method
Barcol Hardness ¹	42		Internal method
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus ²	8730	MPa	ASTM D790
Flexural Strength ³	227	MPa	ASTM D790
Additional Information	Nominal Value	Unit	
Thixotropic Index (25°C)	1.50 - 2.50		
Red Accelerator, Co-oct (Co 6%): .5	%Hardener, MEKPO (PO content, 55%)	: 1%	
Uncured Properties	Nominal Value	Unit	
Density (25°C)	1.11 - 1.13	g/cm³	
Viscosity (25°C)	0.40 - 0.60	Pa·s	
Gel Time (25°C)	8.0 - 15	min	
Cured Properties	Nominal Value	Unit	
Tensile Modulus ⁴	8630	MPa	
Tensile Strength ⁵	128	MPa	
NOTE			
1.	Barcol 934-1 , Unfilled		
2.	Filled		
3.	Filled		
4.	Filled		
5.	Filled		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

