ULTZEX™ 25100J

Linear Low Density Polyethylene

Prime Polymer Co., Ltd.

Message:

ULTZEX™ 25100J is a Linear Low Density Polyethylene product. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America. Applications of ULTZEX™ 25100J include caps/lids/closures, containers and industrial applications.

Characteristics include:

Good Stiffness

High ESCR (Stress Crack Resistant)

General Information			
Features	Good Stiffness		
	High ESCR (Stress Crack Resist.)		
Uses	Caps		
	Containers		
	Industrial Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.924	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	10	g/10 min	ISO 1133
Environmental Stress-Cracking Resistance	200	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, Injection Molded)	57		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	Noninal value	Offic	ISO 527-2
Yield, Injection Molded	9.70	MPa	130 327 2
Break, Injection Molded	> 15.0	MPa	
Tensile Strain (Break, Injection Molded)	> 500	%	ISO 527-2
Flexural Modulus (Injection Molded)	240	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	No Break	Jilit	ISO 179
		Linit	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	98.0	°C	ISO 306
Melting Temperature	120	°C	ISO 11357-3

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

