Lucent PP GPP-130

Polypropylene Homopolymer

Lucent Polymers, Inc.

Message:

30% Glass Fiber Reinforced, Chemically Coupled, Homopolymer Polypropylene Melt Flow Adjustable for Application Colors Available Add "U" for UV Stabilized Add "H" for Heat Stabilized

| General Information | | | |
|--|----------------------------------|-------|-------------|
| Filler / Reinforcement | Glass Fiber,30% Filler by Weight | | |
| Features | Chemically Coupled | | |
| | Homopolymer | | |
| | | | |
| Appearance | Colors Available | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.14 | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow (3.18 mm) | 0.40 | % | |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | 75.8 | МРа | ASTM D638 |
| Tensile Elongation (Break) | 4.0 | % | ASTM D638 |
| Flexural Modulus | 4650 | МРа | ASTM D790 |
| Flexural Strength | 108 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (3.18 mm) | 64 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 141 | °C | ASTM D648 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

