Shin-Etsu Elastomer SV-56000U

Silicone Rubber, HTV

Shin-Etsu Silicones of America

Message:

SV-56000U is one of a series of silicone bases designed for applications requiring high strength.

Excellent mechanical properties

Typical Applications

Molding and extrusion applications for a wide range of products.

| General Information | | | |
|--------------------------------|-------------------|-------|--|
| Features | High strength | | |
| Processing Method | Extrusion | | |
| | Injection molding | | |
| | | | |
| Physical | Nominal Value | Unit | |
| Specific Gravity | 1.18 | g/cm³ | |
| Hardness | Nominal Value | Unit | |
| Durometer Hardness | 60 | | |
| Elastomers | Nominal Value | Unit | |
| Tensile Strength | 10.3 | MPa | |
| Tensile Elongation (Break) | 550 | % | |
| Tear Strength ¹ | 36.8 | kN/m | |
| Compression Set (150°C, 22 hr) | 15 | % | |
| Additional Information | Nominal Value | Unit | |
| Cure Agent | DBPH | | |
| Press / Post Cure: Press | | | |
| Uncured Properties | Nominal Value | Unit | |
| Curing Time | 0.17 | hr | |
| NOTE | | | |
| 1. | B mould | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

