

Kepital® TB-21

Acetal (POM) Copolymer

KEP Americas

Message:

Anti-microbial grade. TB-21 lasts almost permanent effect of anti-microbial. TB-21 can be used in a home appliance and hygiene applications

General Information			
Features	Copolymer		
	Medium Viscosity		
	Microbe Resistant		
Uses	Appliances		
	Personal Care		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR)	9.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break, 23°C)	65.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	35	%	ISO 527-2
Flexural Modulus (23°C)	2550	MPa	ISO 178
Flexural Stress (23°C)	87.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.5	kJ/m ²	ISO 179

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

