

Razalen® R133-02

Polypropylene
Razin™ Engineering Plastics

Message:
Razalen R133-02 is a rubber modified injection grade gray color polypropylene, which is UV stabilized for automotive interior applications.

General Information			
Additive	Rubber		
	UV Stabilizer		
Features	Good UV Resistance		
Uses	Automotive Interior Parts		
Appearance	Grey		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.910	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	23.0	MPa	ASTM D638
Tensile Elongation (Break)	600	%	ASTM D638
Flexural Modulus	1300	MPa	ASTM D790
Flexural Strength	23.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area)			ASTM D256
-20°C	7.00	kJ/m ²	
23°C	40.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	95.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	1.0 to 2.0	hr	
Rear Temperature	180 to 215	°C	
Middle Temperature	180 to 215	°C	
Front Temperature	180 to 215	°C	
Processing (Melt) Temp	180 to 220	°C	
Mold Temperature	30.0 to 60.0	°C	
Injection Pressure	50.0 to 150	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

