# NuSil SFM5-2350

#### Silicone

### NuSil Technology

#### Message:

The Aircraft Industry has used silicone adhesives and coatings for over five decades. Silicone's ability to maintain its elasticity and low modulus over a broad temperature range provides excellent utility in extreme environments. Recent advances in material technology provide more opportunities for the Aircraft engineer in choosing the best material for an intended application. Examples of NuSil's capabilities in custom silicones for Aircraft are demonstrated in the following sections.

Fuel Resistance

Static Dissipation and Electrically Conductive Silicones

Ice-Phobic Coatings

General Purpose: Silicone Foam Comment: Flame Resistant, 25 lb/ft<sup>3</sup> (0.400 g/cm<sup>3</sup>)

General Information			
Features	Electrically Conductive Flame Retardant		
Uses	Aircraft Applications		
	Electrical/Electronic Applications		
	Foam		
Thermoset	Nominal Value	Unit	
Thermoset Components			
Part A	Mix Ratio by Weight: 1.0		
Part B	Mix Ratio by Weight: 1.0		

Fall A	With Ratio by Weight. 1.0	Wix Ratio by Weight, 1.0		
Part B	Mix Ratio by Weight: 1.0	Mix Ratio by Weight: 1.0		
Additional Information	Nominal Value	Unit		
Cure System	Platinum			
Operating Temperature	-50 to 200	°C		
Uncured Properties	Nominal Value	Unit		
Color	Grey			
Density	0.349	g/cm <sup>3</sup>		
Viscosity				
<sup>1</sup>	45	Pa·s		
<sup>2</sup>	55	Pa·s		
Curing Time (100°C)	0.75	hr		
Pot Life	22	min		
Cured Properties	Nominal Value	Unit		
Electric Strength	7.5	kV/mm		
NOTE				
1.	Part B			
2.	Part A			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

