

# PTS PPE-LXS112

Polyphenylene Ether + PS  
Polymer Technology and Services, LLC

Message:

PTS PPE-LXS112 is a Polyphenylene Ether + PS (PPE+PS) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Typical application: Industrial Applications.  
Characteristics include:  
Flame Rated  
Flame Retardant

General Information			
Features	Flame Retardant		
Uses	Industrial Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/5.0 kg)	40	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Break)	60.0	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	25	%	ASTM D638
Flexural Modulus <sup>3</sup>	2350	MPa	ASTM D790
Flexural Strength <sup>4</sup>	90.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area)	16.0	kJ/m <sup>2</sup>	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	120	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.800 mm	V-0		
1.60 mm	V-0		
3.20 mm	V-0		
NOTE			
1.	Type I		
2.	Type I		
3.	2.6 mm/min		
4.	2.6 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT