

Maxiglas® MG515

Polymethyl Methacrylate Acrylic

Maxiglas Corporation

Message:

Maxiglas® is a continuous mass polymerization acrylic pellet that has outstanding optical properties, excellent weather resistance, uniform color and impact resistance. It has exceptional freedom from war page, cracks, scratches, blisters, voids, foreign matter, and other defects which may affect appearance or serviceability.

Applications:

- Extruded sheets for signage, displays and building material
- Automotive parts such as tail lamps, meter covers and sun visors
- General sundries such as tableware, kitchenware, giftware and bathroom accessories
- Optical lenses such as sunglasses, reading glasses and camera lenses
- Light guide panels for LCD displays

General Information			
Features	Good Weather Resistance		
	Opticals		
Uses	Automotive Applications		
	Automotive Backlights		
	Automotive Interior Parts		
	Bathroom Accessories		
	Building Materials		
	Decorative Displays		
	Displays		
	Kitchenware		
	LCD Applications		
	Lighting Applications		
	Optical Applications		
	Toys		
Forms	Pellets		
Processing Method	Compression Molding		
	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	15	g/10 min	ASTM D1238
Water Absorption (24 hr)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method

Tensile Strength	63.7	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	3140	MPa	ASTM D790
Flexural Strength	93.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact	16	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	90.0	°C	ASTM D648
Vicat Softening Temperature	94.0	°C	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		ASTM D542
Transmittance (3000 μm)	93.0	%	ASTM D1003
Haze (3000 μm)	0.30	%	ASTM D1003
Additional Information	Nominal Value	Unit	
Foreign Material ¹	< 0.0500	mm ²	
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 95.0	°C	
Drying Time	4.0	hr	
Rear Temperature	170 to 210	°C	
Middle Temperature	170 to 210	°C	
Front Temperature	170 to 210	°C	
Mold Temperature	30.0 to 50.0	°C	
Injection Pressure	2.76 to 5.52	MPa	
Extrusion	Nominal Value	Unit	
Drying Temperature	70.0 to 95.0	°C	
Drying Time	4.0	hr	
NOTE			
1.	Condition: 50g		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT