# Hostacom EKC 330N E1 D7V721

## Polypropylene Copolymer

### LyondellBasell Industries

#### Message:

Hostacom EKC 330N E1 D7V721 is a 16% talc filled PP copolymer, with good flowability, excellent impact/stiffness balance, good scratch resistance and outstanding blooming resistance at elevated temperatures. The product is also available as a customized color matched, pellet form. This grade is delivered in D7V721 color version.

This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

| General Information                                  |                                   |          |             |
|--|-----------------------------------|----------|-------------|
| Filler / Reinforcement                               | Talc filler, 16% filler by weight |          |             |
| Features   | Low blur phenomenon               |          |             |
|  | Rigid, good                       |          |             |
|  | Copolymer                         |          |             |
|  | Impact resistance, good           |          |             |
|  | Good liquidity                    |          |             |
|  | Scratch resistance                |          |             |
| Uses   | Application in Automobile Field   |          |             |
|  | Car interior equipment            |          |             |
| Appearance   | Available colors                  |          |             |
| Forms  | Particle                          |          |             |
| Processing Method                                    | Injection molding                 |          |             |
| Physical   | Nominal Value                     | Unit     | Test Method |
| Density (23°C)                                       | 1.02                              | g/cm³    | ISO 1183/A  |
| Melt Mass-Flow Rate (MFR) (230°C/2.16<br>kg)         | 18                                | g/10 min | ISO 1133    |
| Mechanical   | Nominal Value                     | Unit     | Test Method |
| Tensile Stress (Yield, 23°C)                         | 21.0                              | MPa      | ISO 527-2   |
| Flexural Modulus <sup>1</sup> (23°C)                 | 1800                              | MPa      | ISO 178/A   |
| Impact   | Nominal Value                     | Unit     | Test Method |
| Charpy Notched Impact Strength                       |                                   |          | ISO 179/1eA |
| -30°C  | 5.0                               | kJ/m²    | ISO 179/1eA |
| 23°C   | 45                                | kJ/m²    | ISO 179/1eA |
| Charpy Unnotched Impact Strength (23°C)              | No Break                          |          | ISO 179/1eU |
| Thermal  | Nominal Value                     | Unit     | Test Method |
| Heat Deflection Temperature (1.8 MPa,<br>Unannealed) | 56.0                              | °C       | ISO 75-2/A  |
|  |                                   |          |             |

#### 1.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

