

# Hifax TRC 134P S82589

Polypropylene Copolymer

LyondellBasell Industries

## Message:

Hifax TCR 134P S82589 is a PP/EPR-Blend, 20% mineral filled, impact modified, UV-stabilized with ultra low shrinkage and high flowability for unpainted exterior applications with metallic look.

General Information			
Filler / Reinforcement	Mineral,20% Filler by Weight		
Additive	Rubber Impact Modifier UV Stabilizer		
Features	High Flow Impact Modified Low Shrinkage		
Uses	Automotive Applications Automotive Bumper Automotive Exterior Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm <sup>3</sup>	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1600	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	5.0	kJ/m <sup>2</sup>	
23°C	40	kJ/m <sup>2</sup>	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT