# apilon 52® FA-6505

### Thermoplastic Polyurethane Elastomer (Polyester)

#### API SpA

#### Message:

apilon 52®FA-6505 is a thermoplastic polyurethane elastomer (polyester)(TPU-polyester) product. It can be processed by injection molding and is available in Europe. apilon 52®FA-6505 application areas include engineering/industrial accessories, electrical/electronic applications, electrical appliances, tools and home applications.

Features include: high liquidity environmental protection/green Good flexibility

low temperature resistance

General Information

Features	No frost								
	Recyclable materials  Good flexibility  High liquidity  Low temperature resistance								
					Uses	Handle			
						Wheels			
Conveyor belt repair									
Electrical/Electronic Applications									
Electrical appliances									
Washer									
Power/other tools									
Pipe fittings									
Household goods									
Sporting goods  Coating application									
				Footwear					
Processing Method	Injection molding								
Physical	Nominal Value	Unit	Test Method						
Specific Gravity	1.17	g/cm³	ASTM D792						
Hardness	Nominal Value	Unit	Test Method						
Durometer Hardness (Shore A, 15 sec)	66		ASTM D2240						
Mechanical	Nominal Value	Unit	Test Method						
Tensile Strength			ASTM D638						
	20.0	MPa	ASTM D638						
100% strain	2.20	MPa	ASTM D638						

300% strain	4.50	MPa	ASTM D638
Tensile Elongation (Break)	950	%	ASTM D638
Abrasion Resistance	60.0	mm³	DIN 53516
Elastomers	Nominal Value	Unit	Test Method
Tear Strength <sup>1</sup>	60.0	kN/m	ASTM D624
Injection	Nominal Value	Unit	
Drying Temperature	80 - 100	°C	
Drying Time	2.0	hr	
Suggested Max Moisture	0.070	%	
Rear Temperature	180 - 190	°C	
Middle Temperature	185 - 200	°C	
Front Temperature	190 - 215	°C	
Nozzle Temperature	200 - 230	°C	
Mold Temperature	30 - 60	°C	
Injection Pressure	50.0 - 100	MPa	
Injection Rate	Slow-Moderate		
NOTE			
1.	With Notch		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

