

ALTECH® PA6 A 2030/109 GF30 BK1132-07LS

Polyamide 6

ALBIS PLASTIC GmbH

Message:

ALTECH® PA6 A 2030/109 GF30 BK1132-07LS is a Polyamide 6 (Nylon 6) product filled with 30% glass fiber. It is available in Asia Pacific, Europe, or North America. Typical application: Housings.

Characteristics include:

Flame Rated

REACH Compliant

RoHS Compliant

Good Mold Release

Heat Stabilizer

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
Features	Good Mold Release		
	Heat Stabilized		
	High Flow		
	Laser Markable		
Uses	Housings		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.60 to 0.80	%	
Flow	0.20 to 0.40	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9000	MPa	ISO 527-2
Tensile Stress (Break)	170	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	8000	MPa	ISO 178
Flexural Stress	240	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	11	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	70	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	200	°C	ISO 75-2/A
Vicat Softening Temperature	200	°C	ISO 306/B50
Flammability	Nominal Value		Test Method

Flame Rating (0.750 mm)	HB	UL 94
Injection	Nominal Value	Unit
Drying Temperature - Desiccant Dryer	80.0	°C
Drying Time - Desiccant Dryer	2.0 to 12	hr
Suggested Max Moisture	0.15	%
Processing (Melt) Temp	270 to 290	°C
Mold Temperature	80.0 to 100	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

