

# Ferro PP RPP30GT13UL NATURAL

Polypropylene  
Ferro Corporation

Message:

Ferro PP RPP30GT13UL NATURAL is a polypropylene material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is injection molding.  
The main features of Ferro PP RPP30GT13UL NATURAL are:  
flame retardant/rated flame  
Flame Retardant

General Information			
Features	Flame retardancy		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.45	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.5	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	44.8	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	4.0	%	ASTM D638
Flexural Modulus			ASTM D790
1% secant: 23°C	5180	MPa	ASTM D790
Tangent: 23°C	5240	MPa	ASTM D790
Flexural Strength (23°C)	68.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	130	J/m	ASTM D256
Unnotched Izod Impact (23°C)	430	J/m	ASTM D4812
Dart Drop Impact (23°C)	0.791	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	149	°C	ASTM D648
1.8 MPa, not annealed	132	°C	ASTM D648
RTI Elec (1.59 mm)	110	°C	UL 746
RTI Imp (1.59 mm)	110	°C	UL 746
RTI (1.59 mm)	110	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Arc Resistance	137	sec	ASTM D495
Comparative Tracking Index (CTI)	600	V	UL 746
High Voltage Arc Tracking Rate (HVTR)	0.00	mm/min	UL 746
Hot-wire Ignition (HWI)	100	sec	UL 746

Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	V-0		UL 94
Additional Information			

The value listed as Comparative Tracking Index was tested in accordance with ASTM D3638.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

