

SABIC® PP PCGR40

Polypropylene Random Copolymer

Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® PP grades for healthcare applications are produced under controlled conditions resulting in high product quality, consistency and a high level of purity.

SABIC® PP PCGR40 is a highly transparent polypropylene random copolymer with good antistatic properties. This grade combines improved aesthetics of the finished articles with low temperature processability and a very good organoleptic performance. Part aesthetics are not affected by the lower temperatures, providing for a broader operating window, enabling short cycle times. SABIC® PP PCGR40 results in excellent demoulding characteristics and has a good stiffness to impact ratio.

Typical applications:

SABIC® PP PCGR40 is typically used for injection moulding of housings for empty disposable 3-part syringes. Other applications demanding a high level of transparency and broad processing window are also possible.

Compliance to regulations:

SABIC® PP PCGR40 complies with the food contact regulations and the relevant monographs of the US Pharmacopoeia.

General Information			
Additive	Clarifier		
	Antistatic property		
Features	High purity		
	Antistatic property		
	Fast molding cycle		
	Good sensory characteristics		
	Definition, high		
	Compliance of Food Exposure		
	Good demoulding performance		
	Random copolymer		
Uses	Shell		
	Medical/nursing supplies		
Agency Ratings	USP Not Rated		
Appearance	Clear/transparent		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.905	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	40	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1150	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	29.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	13	%	ISO 527-2/1A/50

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
0°C	2.0	kJ/m ²	ISO 179/1eA
23°C	4.5	kJ/m ²	ISO 179/1eA
Notched Izod Impact			ISO 180/1A
0°C	2.0	kJ/m ²	ISO 180/1A
23°C	4.0	kJ/m ²	ISO 180/1A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

