# Lucky Enpla LMF3250

## Polybutylene Terephthalate Lucky Enpla Co LTD

#### Message:

Lucky Enpla LMF3250 is a polybutene terephthalate (PBT) product, which contains 25% mineral fillers. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region. Typical application areas are: automotive industry. The main characteristics are: beautiful.

General Information			
Filler / Reinforcement	Mineral filler, 25% filler by	weight	
Features	Excellent appearance		
Uses	Application in Automobile Field		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.54	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.50 - 1.2	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup>	53.9	MPa	ASTM D638
Flexural Modulus <sup>2</sup>	5200	MPa	ASTM D790
Flexural Strength <sup>3</sup>	93.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (3.18 mm)	34	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	200	°C	ASTM D648
1.8 MPa, not annealed	105	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	70.0 - 90.0	°C	
Drying Time	2.0 - 3.0	hr	
Rear Temperature	220 - 240	°C	
Middle Temperature	230 - 250	°C	
Front Temperature	240 - 260	°C	
Nozzle Temperature	250 - 265	°C	
Mold Temperature	80.0 - 110	°C	
Back Pressure	0.490 - 2.94	MPa	
Screw Speed	30 - 60	rpm	
Injection instructions			
Resin Temperature: 230-250°CInjection P	ressure (1st Pressure): 700-1200 k	g/cm²Injection Pressure (2nd Pre	essure): 400-800 kg/cm²
NOTE			
1.	10 mm/min		
2.	3.0 mm/min		

3. 3.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

