

Latishield 87/28-10A

Polycarbonate

LATI S.p.A.

Message:

EMI shielding product based on Polycarbonate (PC).
Steel fibres.

General Information			
Filler / Reinforcement	Steel		
Features	Electromagnetic Shielding (EMI)		
Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.60 to 0.75	%	
Flow : 2.00 mm	0.55 to 0.75	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3100	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	50.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	12	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Notched Izod Impact (23°C, 3.20 mm)	65	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	140	°C	ISO 75-2/B
1.8 MPa, Unannealed	135	°C	ISO 75-2/A
Vicat Softening Temperature	145	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	3.0E+2	ohms	ASTM D257
Electromagnetic Reflection	95	%	
Injection	Nominal Value	Unit	
Drying Temperature	110 to 130	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	265 to 300	°C	
Mold Temperature	80.0 to 100	°C	
Injection Rate	Moderate		
NOTE			

1. at 60 Mpa of cavity pressure

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

