ENVIROLOY® ENV15-NC330

Polycarbonate + ABS ENVIROPLAS®, Inc.

Message:

Injection Molding Grade, High Heat Resistance, Excellent Processability, RoHS Compliant NC330 = To Be Assigned 5 Digit Number Indicating Natural, Black, or Custom Color. The ENV15 Series Products Are Available With Mold Release and/or UV Stabilizer. Contact Enviroplas Regarding UL Recognized Versions Of This Product.

| General Information | | | | |
|--|----------------------|----------|-----------------|--|
| Features | Good Processability | | | |
| | High Heat Resistance | | | |
| RoHS Compliance | RoHS Compliant | | | |
| Appearance | Black | | | |
| | Colors Available | | | |
| | Natural Color | | | |
| Forms | Pellets | | | |
| Processing Method | Injection Molding | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Specific Gravity | 1.15 | g/cm³ | ASTM D792 | |
| Melt Mass-Flow Rate (MFR) (260°C/5.0 kg) | 12 | g/10 min | ASTM D1238 | |
| Molding Shrinkage - Flow | 0.50 to 0.70 | % | ASTM D955 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Strength (Yield) | 54.5 | MPa | ASTM D638 | |
| Flexural Modulus | 2280 | MPa | ASTM D790 | |
| Flexural Strength | 88.3 | MPa | ASTM D790 | |
| Impact | Nominal Value | Unit | Test Method | |
| Notched Izod Impact (23°C) | 640 | J/m | ASTM D256 | |
| Thermal | Nominal Value | Unit | Test Method | |
| Deflection Temperature Under Load | | | ASTM D648 | |
| 0.45 MPa, Unannealed | 127 | °C | | |
| 1.8 MPa, Unannealed | 108 | °C | | |
| Flammability | Nominal Value | | Test Method | |
| Flame Rating (1.50 mm) | НВ | | Internal Method | |
| Injection | Nominal Value | Unit | | |
| Drying Temperature | 82.2 | °C | | |
| Drying Time | 3.0 to 4.0 | hr | | |
| Suggested Max Moisture | 0.050 | % | | |
| Rear Temperature | 238 to 260 | °C | | |
| | | | | |

| Middle Temperature | 243 to 271 | °C |
|--------------------|----------------|-----|
| Front Temperature | 249 to 277 | °C |
| Nozzle Temperature | 243 to 271 | °C |
| Mold Temperature | 76.7 to 98.9 | °C |
| Injection Rate | Moderate-Fast | |
| Back Pressure | 0.345 to 0.689 | MPa |
| Screw Speed | 40 to 70 | rpm |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

