

VESTAMID® L L-R7-MHI

Polyamide 12
Evonik Industries AG

Message:

Permanently antistatic and electrically conductive polyamide 12 compounds
Characterization: medium viscosity, heat- and light-stabilized, increased cold impact strength, with processing aid; especially designed for parts meeting EN 50014
Application Examples: antistatic and electrically conductive moldings or extrudates for use in areas prone to explosion such as coal mining and other industries, e.g., housings for explosion-protected measurement equipment and switches, ventilation fans for electric motors, chair castors, loud speaker boxes, telephone and radio equipment, profiles for assembly lines, also with electric shock protection
The properties of PA 12 compounds can be modified to suit the requirements of many applications by incorporating various additives such as stabilizers, plasticizers, reinforcements, and fillers.
The VESTAMID® L compounds of Evonik comprise a range of various products that are customized to the requirements of processors and users. Many of the PA 12 compounds are suitable especially for the injection molding of recision parts; others have been developed specifically for the extrusion process.

General Information	
Additive	Heat Stabilizer
	Processing Aid
	UV Stabilizer
Features	Antistatic
	Electrically Conductive
	Fatigue Resistant
	Food Contact Acceptable
	Fuel Resistant
	Good Abrasion Resistance
	Good Impact Resistance
	Good Processability
	Grease Resistant
	Heat Stabilized
	High ESCR (Stress Crack Resist.)
	Light Stabilized
	Low to No Water Absorption
	Medium Viscosity
	Oil Resistant
	Solvent Resistant
	Sound Damping
	Vibration Damping
Uses	Electrical/Electronic Applications
	Housings
	Mining Applications
	Profiles

Agency Ratings	EU 10/2011		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.08	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	1.5	%	
Flow	1.4	%	
Water Absorption			ISO 62
Saturation, 23°C	1.5	%	
Equilibrium, 23°C, 50% RH	0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1400	MPa	ISO 527-2
Tensile Stress (Yield)	36.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	6.0	%	
Break	> 50	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C, Complete Break	12	kJ/m ²	
23°C, Partial Break	60	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	130	°C	ISO 75-2/B
1.8 MPa, Unannealed	50.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	175	°C	ISO 306/A
--	140	°C	ISO 306/B
Melting Temperature ¹	178	°C	ISO 11357-3
CLTE - Flow (23 to 55°C)	1.7E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+7	ohms · cm	IEC 60093
Insulation Resistance	1.0E+7	ohms	IEC 60167
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
Additional Information	Nominal Value		Test Method

ISO Shortname	PA12-HI, MHZ, 16-010	ISO 1874
NOTE		

1. 2nd Heating

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

