

# Huaфон JF-S-DR9030

Polyurethane  
Huaфон Group Co., Ltd.

Message:  
Special Type for Surface Layer  
Characteristics  
Special resin for Yangbuck Leather, solvent resistance, swelling resistance, good fastness.  
Applications  
Yangbuck foaming

General Information		
Features	Foamable	
	Solvent Resistant	
Uses	Foam	
Additional Information	Nominal Value	Unit
Solvents	DMF/MEK/TOL	
Uncured Properties	Nominal Value	Unit
Solids Content	29 to 31	%
Viscosity (25°C)	100 to 160	Pa·s
Cured Properties	Nominal Value	Unit
Tensile Modulus (100% Secant)	2.00 to 3.00	MPa
Tensile Strength	> 20.0	MPa
Tensile Elongation at Break	> 500	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT