

Devcon Plastic Welder™ White

Epoxy; Epoxide

Devcon

Message:

Toughened structural adhesive, after curing, produces superior strength load-bearing bonds to engineered plastics.

Intended Use:

Bond: PVC, fiberglass, ABS, FRT, PPO, PCBB, Metton®, Lomod®, Valox®, Noryl®, GTX, Minlon®, epoxy, RIM urethane, wood, poorly prepared surfaces, and where outdoor weathering or solvent exposure is anticipated.

Features:

Minimal surface preparation

Room temperature cure

1:1 mix ratio

Rapid fixture in thin set

Non-sagging formula

General Information			
Features	Solvent resistance		
	Adhesiveness		
	Good weather resistance		
Uses	Bonding		
	Adhesive		
Appearance	White		
Physical	Nominal Value	Unit	Test Method
Specific Volume	0.911	cm ³ /g	
Solid content-by Volume	100	%	
Impact Resistance	11.7	J/cm	
Service Temperature	-55 - 121	°C	
Work Time (22°C)	2.0 - 3.0	min	
Tensile Shear Adhesion			ASTM D1002
ABS	8.96	MPa	ASTM D1002
GBS	20.7	MPa	ASTM D1002
Polycarb	9.65	MPa	ASTM D1002
Density ¹	1.10	g/cm ³	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	78		ASTM D2240
Mechanical	Nominal Value	Unit	
Tensile Elongation (Break)	15 - 25	%	
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			

Mixing ratio by weight: 1.0

Component a

Mixing ratio by capacity: 1.0

Mixing ratio by weight: 1.0

Component B

Mixing ratio by capacity: 1.0

Thermoset Mix Viscosity	50000	cP
-------------------------	-------	----

Additional Information	Nominal Value	Unit	Test Method
------------------------	---------------	------	-------------

Cured 7 days @ 75°F

Uncured Properties	Nominal Value	Unit	Test Method
--------------------	---------------	------	-------------

Curing Time	24	hr
-------------	----	----

NOTE

1. Mixed

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT