

# Color-in™ MA504-M

Polymethyl Methacrylate Acrylic

Shanghai KumhoSunny Plastics Co., Ltd.

Message:

MA504-M is super weather resistance a molding aesthetic resin.MA504-M has many properties:(1)high flow(2)high gloss(3)anti-scratch(4)recycling.MA504-M is mainly used in appearance items of household appliance,etc.

General Information			
Features	Good Weather Resistance		
	High Flow		
	High Gloss		
	Pleasing Surface Appearance		
	Recyclable Material		
	Scratch Resistant		
Uses	Appliances		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.17	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Pencil Hardness - 500g	2H		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	70.0	MPa	ASTM D638
Flexural Modulus	2500	MPa	ASTM D790
Flexural Strength	85.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	40	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	80.0	°C	ASTM D648
Vicat Softening Temperature	92.0	°C	ASTM D1525 <sup>1</sup>
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94

Optical	Nominal Value	Test Method
Gardner Gloss	> 85	ASTM D523
Injection	Nominal Value	Unit
Drying Temperature	80.0 to 85.0	°C
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.050	%
Rear Temperature	190 to 210	°C
Middle Temperature	210 to 220	°C
Front Temperature	230 to 240	°C
Nozzle Temperature	225 to 235	°C
Processing (Melt) Temp	230 to 240	°C
Mold Temperature	60.0 to 80.0	°C
Back Pressure	1.00 to 5.00	MPa
Screw Speed	30 to 50	rpm
NOTE		
1.	Rate B (120°C/h)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

