ARCEL® ULV (1.25 pcf)

Polystyrene + PE

NOVA Chemicals

Message:

ARCEL® ULV (1.25 pcf) is a Polystyrene + PE (PS+PE) material. It is available in North America for foam processing.

| General Information | | | |
|---------------------------------|-----------------|-------|-------------|
| Appearance | Natural Color | | |
| | White | | |
| | | | |
| Forms | Spheres | | |
| Processing Method | Foam Processing | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.0200 | g/cm³ | ASTM D3575 |
| Particle Size - 98% | 0.900 to 2.00 | mm | |
| VOC Content | | | |
| Pentane | 5.5 | % | |
| Plasticizer | 0.30 | % | |
| Flexural Strain | 11 | % | ASTM C203 |
| Puncture | 168 | N | ASTM D3763 |
| Tear Strength - at Maximum Load | 1.5 | kN/m | ASTM D3575 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | 0.288 | MPa | ASTM D3575 |
| Flexural Strength | | | ASTM C203 |
| | 0.273 | MPa | |
| 5.0% Strain | 0.241 | MPa | |
| Compressive Strength | | | ASTM D3575 |
| 10% Strain | 0.114 | MPa | |
| 25% Strain | 0.132 | MPa | |
| 50% Strain | 0.191 | MPa | |
| 75% Strain | 0.412 | MPa | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 134247555

Phone: +86 13424755533 Email: sales@su-jiao.com No. 215, Lianhe North Road, Fengxian District, Shanghai, China

