Axiall PVC 1701

Flexible Polyvinyl Chloride Axiall Corporation

Message:

1701 is a flexible extrusion PVC compound formulated for exceptional clarity in USP Class VI applications. The compound possesses excellent color retention in applications requiring gamma radiation sterilization.

General Information			
Features	Good flexibility		
	Definition, high		
	Deminion, riigh		
Agency Ratings	USP Class VI		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20 - 1.24	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (175°C/14.9			
kg)	46	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	67 - 73		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
	17.6	MPa	ASTM D638
100% strain	6.89	MPa	ASTM D638
Tensile Elongation (Break)	410	%	ASTM D638
Thermal	Nominal Value	Unit	
Melting Temperature	171	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

