

Kingfa FRHIPS-117

High Impact Polystyrene

Kingfa

Message:

Kingfa FRHIPS-117 is a High Impact Polystyrene material. It is available in Asia Pacific or North America.

Important attributes of Kingfa FRHIPS-117 are:

Flame Rated

Flame Retardant

High Flow

Impact Resistant

Typical applications include:

Housings

Appliances

Household Applications

General Information			
UL YellowCard	E171666-225768		
Features	Flame Retardant		
	High Flow		
	High Impact Resistance		
Uses	Appliances		
	Electrical Housing		
	Household Goods		
	Housings		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow (23°C)	0.40 to 0.60	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	91		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (23°C, Injection Molded)	23.0	MPa	ASTM D638
Tensile Elongation ² (Break, 23°C, Injection Molded)	40	%	ASTM D638
Flexural Modulus ³ (23°C, Injection Molded)	2000	MPa	ASTM D790
Flexural Strength ⁴ (23°C, Injection Molded)	34.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm, Injection Molded)	95	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	75.0	°C	ASTM D648
Vicat Softening Temperature	93.0	°C	ASTM D1525 ⁵
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		
3.00 mm	V-0		
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	2.0 mm/min		
4.	2.0 mm/min		
5.	Rate B (120°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

