

DynaMix™ 3201-HF

Polyetheretherketone

Polymer Dynamix

Message:

High Flow PEEK

Features:

Excellent Chemical Resistance

Ideal for Thin Wall Molding

Good Dimensional Stability

Applications

Automotive

Industrial

Military

General Information			
Features	Good Chemical Resistance		
	Good Dimensional Stability		
	High Flow		
Uses	Automotive Applications		
	Industrial Applications		
	Military Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (400°C/2.16 kg)	35 to 39	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	100	MPa	
Break	100	MPa	
Tensile Elongation			ASTM D638
Yield	5.0 to 6.0	%	
Break	10 to 20	%	
Flexural Modulus	3790	MPa	ASTM D790
Flexural Strength	152	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	320	°C	ASTM D648
Injection	Nominal Value	Unit	

Drying Temperature	138 to 149	°C
Drying Time	3.0 to 5.0	hr
Rear Temperature	343 to 360	°C
Middle Temperature	357 to 371	°C
Front Temperature	366 to 382	°C
Nozzle Temperature	366 to 382	°C
Processing (Melt) Temp	366 to 382	°C
Mold Temperature	177 to 204	°C
Injection Rate	Moderate	
Screw Speed	40 to 70	rpm
Clamp Tonnage	4.1 to 6.9	kN/cm ²

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

