

Elastollan® R 3000

Thermoplastic Polyurethane Elastomer (Polyester)

BASF Polyurethanes GmbH

Message:

Glass fibre reinforced thermoplastic Polyester Polyurethane Elastomers with excellent mechanical properties, outstanding impact strength, high stiffness whilst maintaining good elongation, low coefficient of expansion similar to Aluminium, low shrinkage, good paintability.
Typical applications
Automotive body and panels and structural door trim parts, under body sealants, technical mouldings e.g. plugs, ski tips.

General Information			
UL YellowCard	E140250-222878		
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	High Impact Resistance		
	High Stiffness		
	Low Shrinkage		
	Paintable		
Uses	Automotive Exterior Parts		
	Automotive Exterior Trim		
	Plugs		
	Sealants		
	Sporting Goods		
Appearance	Natural Color		
Processing Method	Injection Molding		
Multi-Point Data	Creep Modulus vs. Time (ISO 11403-1)		
	Isochronous Stress vs. Strain (ISO 11403-1)		
	Shear Modulus vs. Temperature (ISO 11403-1)		
Physical	Nominal Value	Unit	Test Method
Density	1.38	g/cm ³	ISO 1183/A
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 3 sec)	73		ISO 7619
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2800	MPa	ISO 527-2
Tensile Stress	80.0	MPa	ISO 527-2/1A/50
Tensile Strain (Break)	10	%	ISO 527-2/1A/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	10	kJ/m ²	
23°C	30	kJ/m ²	

Charpy Unnotched Impact Strength			ISO 179
-30°C	70	kJ/m²	
23°C	120	kJ/m²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	155	°C	ISO 75-2/B
1.8 MPa, Unannealed	120	°C	ISO 75-2/A
CLTE - Flow (23 to 80°C)	2.0E-5	cm/cm/°C	DIN 53752-A
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	225 to 245	°C	
Mold Temperature	50.0 to 70.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

