

NEOFLON™ AC-5500

Perfluoroalkoxy
DAIKIN AMERICA, INC.

Message:
NEOFLON™AC-5500 is a perfluoroalkoxy (PFA) material. This product is available in North America.

General Information			
Forms	Powder		
Physical	Nominal Value	Unit	Test Method
Apparent Density	0.55	g/cm ³	ASTM D1895
Melt Mass-Flow Rate (MFR) (372°C/5.0 kg)	7.0	g/10 min	ASTM D1238
Thermal	Nominal Value	Unit	
Melting Temperature	308	°C	
Additional Information			

The value listed as Apparent Density, ASTM D1895, was tested in accordance with JIS K6891Particle Size, Daikin testing method: 20-70 MicronsThe values listed as Melting Point and Melt Flow Rate were tested in accordance with ASTM D3307

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

