

# Styropor® P-340C H

Expanded Polystyrene

BASF Corporation

## Message:

### Products and their uses

Styropor P-340C H non-modified product can be used in a wide variety of shape molding applications, typically 1.0 lbs/ft<sup>3</sup> density with excellent fusion and short cycle time. Protective packaging - leak resistant applications such as coolers not requiring modified material.

### Description

Regular non-modified expandable polystyrene (EPS) containing approximately 5.2 - 5.8 wt.% pentane as the blowing agent. The P-340C H is supplied as spherical beads with a bulk density of approximately 40 lbs/ft<sup>3</sup> (640 kg/m<sup>3</sup>).

Styropor P-340C H product is compatible with many anti-stat, mineral oil and color additives added during processing. P-340C H product does not contain chlorofluorocarbons or flame retardants.

General Information		
Additive	Blowing Agent (5 to 6%) 2	
Features	Fast Molding Cycle	
Uses	Foam	
	Packaging	
Agency Ratings	EC 1907/2006 (REACH)	
RoHS Compliance	RoHS Compliant	
Forms	Spheres	
Physical	Nominal Value	Unit
Density <sup>1</sup>	0.0160 to 0.0481	g/cm <sup>3</sup>
Apparent Density	0.64	g/cm <sup>3</sup>
Additional Information	Nominal Value	Unit
Bead Size	600.0 to 1250.0	µm
Pre-Puff Age - dependent on density	4.0 to 24.0	hr
NOTE		

1. Typical densities are first and/or double pass pre-expansion.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT