

# Manner Flexible PVC 6914 NA023

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

## Message:

Recommended Applications: Non-Lead Heat Stabilized 85°C Automotive Extrusion Compound for use in SAE J1128, GPT and TWP applications. This compound is RoHS compliant.

General Information			
Additive	Heat Stabilizer		
Features	Heat Stabilized		
	Low (to None) Lead Content		
Uses	Automotive Applications		
	Wire & Cable Applications		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.29 to 1.33	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	37 to 43		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	19.3	MPa	ASTM D638
Tensile Elongation (Break)	300	%	ASTM D638
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	175 to 180	°C	
Cylinder Zone 3 Temp.	175 to 180	°C	
Cylinder Zone 5 Temp.	175 to 180	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

