# Formolene® 5140L

#### Polypropylene Homopolymer

Formosa Plastics Corporation, U.S.A.

#### Message:

Formolene 5140L is a highly nucleated polypropylene homopolymer designed for general purpose injection molding applications including closures, packaging, small appliances, housewares and toys. It contains a unique combination of stabilizers, which provides excellent processability with good stiffness, environmental stress crack resistance, heat performance and minimal odor & taste.

Formolene 5140L meets all requirements of the U. S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. It does meet the standards of the FDA status "A".

General Information					
Additive	Nucleating Agent				
	Unspecified Stabilizer				
Features	Food Contact Acceptable				
	General Purpose				
	Good Processability				
	Good Stiffness				
	High ESCR (Stress Crack Resist.)				
	Homopolymer				
	Low to No Odor				
	Low to No Taste				
	Nucleated				
Uses	Closures				
	Household Goods				
	Packaging				
	Toys				
	White Goods & Small Appliances				
Agency Ratings	EC 1907/2006 (REACH)				
	FDA 21 CFR 177.1520				
Forms	Pellets				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Density	0.900	g/cm³	ASTM D1505		
Melt Mass-Flow Rate (MFR) (230°C/2.16					
kg)	5.5	g/10 min	ASTM D1238		
Hardness	Nominal Value	Unit	Test Method		
Rockwell Hardness (R-Scale, Injection Molded)	108		ASTM D785		

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield, Injection Molded)	39.3	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Yield, Injection	7.0	%	ASTM D638
Molded)  Flexural Modulus - 1% Secant <sup>3</sup> (Injection	7.0	76	ASTIVI D036
Molded)	1930	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection			
Molded)	48	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45			
MPa, Unannealed, Injection Molded)	123	°C	ASTM D648
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

