

ColorFast® FRPS200

High Impact Polystyrene
LTL Color Compounders, Inc.

Message:
V0/5VA high impact styrene

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	High Impact Resistance		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	6.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.30 to 0.60	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (L-Scale)	61		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	24.1	MPa	
Break	24.8	MPa	
Tensile Elongation ² (Break)	35	%	ASTM D638
Flexural Modulus ³	2000	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	96	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.35 mm)	86.1	°C	ASTM D648
Flammability	Nominal Value		Test Method
	V-0		
Flame Rating	5VA		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	71.1	°C	
Drying Time	2.0 to 4.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Shot Size	40 to 60	%	

Rear Temperature	171 to 199	°C
Middle Temperature	193 to 227	°C
Front Temperature	218 to 254	°C
Nozzle Temperature	204 to 232	°C
Processing (Melt) Temp	204 to 238	°C
Mold Temperature	10.0 to 71.1	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm
Vent Depth	0.025 to 0.076	mm

NOTE

- | | |
|----|-----------|
| 1. | 51 mm/min |
| 2. | 51 mm/min |
| 3. | 51 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

