

Titacon® ST220

Acetal (POM) Copolymer

Titan Plastics Compounds Co., Ltd.

Message:

Titacon® ST220 is a polyoxymethylene (POM) copolymer material. This product is available in the Asia-Pacific region and is processed by extrusion.

Titacon® The main features of ST220 are:

flame retardant/rated flame

Antistatic

Wear-resistant

General Information			
Additive	Antistatic property		
Features	Good coloring		
	Good wear resistance		
	No shedding		
Appearance	Light beige		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.35	g/cm ³	ISO 1183
Molding Shrinkage ¹ (3.00 mm)	1.8 - 2.2	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	40.0	MPa	ISO 527-2
Tensile Strain (Break)	> 30	%	ISO 527-2
Flexural Modulus	1700	MPa	ISO 178
Flexural Stress	55.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	25	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	75.0	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+8	ohms	IEC 60093
Volume Resistivity	1.0E+9	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	170 - 200	°C	
Mold Temperature	60.0 - 100	°C	
Injection instructions			

Injection Pressure: 30 to 70% Injection Velocity: 20 to 50%

NOTE

1. 50x70x3 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

