

Argothane® 19103

Thermoplastic Polyurethane Elastomer

Argotec LLC

Message:

- Applications:
- Textile lamination
- Characteristics:
- Smooth surface
 - Hard ether
 - High softening temperature

General Information			
Features	High Hardness		
Uses	Laminates		
	Textile Applications		
Processing Method	Blown Film		
Hardness	Nominal Value	Test Method	
Durometer Hardness (Shore A)	92	ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance (1000 Cycles, 1000 g, H-22 Wheel)	50.0	mg	ASTM D1044
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	9.90	MPa	
300% Strain	18.6	MPa	
Tensile Strength	35.5	MPa	ASTM D412
Tensile Elongation (Break)	520	%	ASTM D412
Tear Strength ¹	94.6	kN/m	ASTM D624
NOTE			

1. Die C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT