

PLANAC BT-1000

Polybutylene Terephthalate

TOYOBO America, Inc.

Message:

PLANAC BT-1000 is a polybutene terephthalate (PBT) product. It can be processed by injection molding and is available in North America or Asia Pacific. The main characteristics are: flame retardant/rated flame.

General Information			
UL YellowCard	E51743-100754847		
Features	General		
Uses	General		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	1.5	%	ASTM D955
Transverse flow	1.9	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.080	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	117		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2800	MPa	ASTM D638
Tensile Strength	55.0	MPa	ASTM D638
Tensile Elongation (Break)	280	%	ASTM D638
Flexural Modulus	2300	MPa	ASTM D790
Flexural Strength	90.0	MPa	ASTM D790
Compressive Strength	84.0	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	45	J/m	ASTM D256
Unnotched Izod Impact	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	160	°C	ASTM D648
1.8 MPa, not annealed	70.0	°C	ASTM D648
CLTE - Flow (-30 to 100°C)	9.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength (1.60 mm)	26	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.30		ASTM D150

Dissipation Factor (1 MHz)	0.020		ASTM D150
Arc Resistance	160	sec	ASTM D495
Comparative Tracking Index (CTI)	600	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94

Additional Information

The value shown for Comparative Track Index, UL 746, was tested in accordance with ASTM D3638.Flexural Elongation @ Break, ASTM D790: NB

Injection	Nominal Value	Unit
Rear Temperature	230 - 260	°C
Middle Temperature	230 - 260	°C
Front Temperature	230 - 260	°C
Mold Temperature	20.0 - 70.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

