

Toughblend® PA66-1600

Polyamide 6

Colour Image Plastic Compound Sdn. Bhd. (CIPC)

Message:

Toughblend® PA66-1600 is a glass fiber reinforced compound characterized by excellent thermal and mechanical properties.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Uses	Automotive Applications		
	Industrial Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	190	MPa	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Flexural Modulus	9250	MPa	ASTM D790
Flexural Strength	275	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 4.00 mm)	260	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating (1.60 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	4.0 to 8.0	hr	
Rear Temperature	275 to 280	°C	
Middle Temperature	280 to 285	°C	
Front Temperature	285 to 290	°C	
Nozzle Temperature	290 to 295	°C	
Processing (Melt) Temp	275 to 295	°C	
Mold Temperature	70.0 to 100	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT