

Sindustris PC GN5002RFP

Polycarbonate
Sincerity Australia Pty Ltd.

Message:

Sindustris PC GN5002RFP is a Polycarbonate (PC) material. It is available in Asia Pacific for injection molding.

Important attributes of Sindustris PC GN5002RFP are:

Flame Rated
Flame Retardant
Halogen Free
Heat Resistant

Typical applications include:

Housings
Electrical/Electronic Applications

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogen Free		
	High Heat Resistance		
Uses	Electrical Housing		
	Electrical/Electronic Applications		
	Housings		
	Television Housings		
UL File Number	E306922		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	65.7	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	80	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	2750	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	98.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 6.40 mm)	110	°C	ASTM D648
RTI Elec	80.0	°C	UL 746

RTI Imp	80.0	°C	UL 746
RTI Str	85.0	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.20 mm	V-0		
2.50 mm	V-0		
3.00 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	85.0 to 95.0	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	240 to 265	°C	
Middle Temperature	250 to 270	°C	
Front Temperature	255 to 275	°C	
Nozzle Temperature	260 to 280	°C	
Processing (Melt) Temp	260 to 280	°C	
Mold Temperature	70.0 to 90.0	°C	
Back Pressure	0.200 to 0.600	MPa	
Screw Speed	40 to 70	rpm	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	10 mm/min		
4.	10 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

