

Torayca® 2701T-30V

Polyamide 610

Toray Resin Company

Message:

Torayca® 2701T-30V is a Polyamide 610 (Nylon 610) product filled with 20% carbon fiber. It is available in Asia Pacific, Europe, or North America. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Carbon Fiber,20% Filler by Weight		
Part Marking Code	>PA610-CF20<		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.22	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 3.00 mm ¹	0.50	%	
Flow : 3.00 mm ²	0.10	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	1.1	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (23°C)	264	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.2	%	ISO 527-2
Flexural Modulus (23°C)	20000	MPa	ISO 178
Flexural Stress (23°C)	398	MPa	ISO 178
Amount of Wear - vs. S45C ³	0.300	mg/hr	Suzuki Method
Coefficient of Friction - vs. S45C ⁴	0.360		Suzuki Method
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	210	°C	ISO 75-2/A
Melting Temperature	225	°C	DSC
CLTE - Flow	1.5E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+3	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
NOTE			
1.	80x80x3		
2.	80x80x3mm		
3.	1MPa, 0.33 m/s		
4.	1MPa, 0.33 m/s		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

