

# EVALENE® LLDPE LF20184

Linear Low Density Polyethylene  
JG Summit Petrochemical Corporation

Message:

LLDPE is used for heavy-duty sacks, lamination films, industrial cosmetics, pharmaceutical and food packaging materials. Low Heat Seal Temperatures. Strong Seals. Excellent Tear, Puncture and Impact Strengths. These properties make Evalene® the best choice for LLDPE packaging films. Its outstanding environmental stress crack resistance, good impact properties at low temperatures, and warp resistance also make it attractive for injection molding applications.

General Information			
Additive	High Slip		
	Medium Antiblock		
Features	Good Tear Strength		
	High Clarity		
	High ESCR (Stress Crack Resist.)		
	High Impact Resistance		
	High Slip		
	Low Temperature Heat Sealability		
	Low Temperature Impact Resistance		
	Medium Antiblocking		
	Puncture Resistant		
	Warp Resistant		
Uses	Film		
	Food Packaging		
	Industrial Applications		
	Liners		
	Stretch Wrap		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Blown Film		
	Film Extrusion		
	Rotational Molding		
Physical	Nominal Value	Unit	Test Method
Density <sup>1</sup>	0.918	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method

Film Thickness - Tested	25	μm	
Secant Modulus <sup>2</sup>			ASTM D882
MD : 25 μm, Blown Film	190	MPa	
TD : 25 μm, Blown Film	200	MPa	
Tensile Strength <sup>3</sup>			ASTM D882
MD : Break, 25 μm,Blown Film	19.0	MPa	
TD : Break, 25 μm,Blown Film	15.0	MPa	
Tensile Elongation <sup>4</sup>			ASTM D882
MD : Break, 25 μm,Blown Film	650	%	
TD : Break, 25 μm,Blown Film	600	%	
Dart Drop Impact (25 μm, Blown Film)	85	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 25 μm, Blown Film	160	g	
TD : 25 μm, Blown Film	260	g	

#### NOTE

1. Density is that of the base polymer.  
Final density is higher due to the presence of antiblock

2. 25 mm/min

3. 500 mm/min

4. 500 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT