## Unipren® Elastomers B3 PRTA010 70A EG06S1 UP341

Polypropylene + EPDM Rubber

Petropol Industry and Trade of Polymers LTDA

## Message:

Unipren® Elastomers B3 PRTA010 70A EG06S1 UP341 is a Polypropylene + EPDM Rubber (PP+EPDM) material. It is available in Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of Unipren® Elastomers B3 PRTA010 70A EG06S1 UP341 are:

Good Weather Resistance

**Heat Resistant** 

Typical applications include:

**High Temperature Applications** 

**Outdoor Applications** 

General Information				
Features	Good Weather Resistance			
	High Heat Resistance			
Uses	High Temperature Applications			
	Outdoor Applications			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	0.980	g/cm³	ASTM D792	
Molding Shrinkage - Flow	2.0 to 3.0	%	ASTM D955	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	67 to 73		ASTM D2240	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Stress <sup>1</sup>			ASTM D412	
100% Strain	2.70	MPa		
300% Strain	4.10	MPa		
Tensile Strength <sup>2</sup> (Break)	7.50	MPa	ASTM D412	
Tensile Elongation <sup>3</sup> (Break)	460	%	ASTM D412	
Tear Strength <sup>4</sup>	35.0	kN/m	ASTM D624	
Compression Set (70°C, 22 hr)	37	%	ASTM D395B	
Injection	Nominal Value	Unit		
Drying Temperature	80.0	°C		
Drying Time	2.0	hr		
Processing (Melt) Temp	160 to 185	°C		
Mold Temperature	20.0 to 50.0	°C		
NOTE				

1.	Die C	
2	Die C	
2.	Dic C	
2	Die C	
5.	Die C	
4	D:- D	
4.	Die B	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

