

INDURE™ X225-UV DK SHADOW

Polyolefin

LyondellBasell Industries

Message:

Indure X225-UV DK SHADOW engineered polyolefin material is typically used for large, molded-in-color automotive applications that require ductile impact properties at low temperatures, UV resistance and good processability.

General Information			
Features	Good UV resistance		
	Workability, good		
	Scratch resistance		
	ductility		
Uses	Car anti-collision bar		
	Application in Automobile Field		
	Automotive exterior parts		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	40	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 4.00 mm)	26.0	MPa	ISO 527-2/50
Flexural Modulus ¹ (4.00 mm)	1350	MPa	ISO 178
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT