

STERLENE™ BMV212W

Thermoplastic Polyolefin Elastomer

R&P; (Pte.) Ltd.

Message:

STERLENE™ BMV212W is a compounded mineral filled polypropylene (TPO) for injection molding, with high impact, high stiffness and good UV resistance, suitable for automotive exterior application.

General Information			
Filler / Reinforcement	Mineral		
Features	Good Impact Resistance		
	Good Stiffness		
	Good UV Resistance		
Uses	Automotive Applications		
	Automotive Exterior Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.06	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) ¹ (230°C/2.16 kg)	35	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2360	MPa	ISO 527-2/50
Tensile Stress (Yield, 23°C)	20.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield, 23°C	5.7	%	
Break, 23°C	49	%	
Flexural Modulus ² (23°C)	2040	MPa	ISO 178
Flexural Stress ³ (23°C)	30.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C, Partial Break)	31	kJ/m ²	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	56.0	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Time	2.0	hr	
Processing (Melt) Temp	190 to 240	°C	
Mold Temperature	25.0 to 60.0	°C	
NOTE			
1.	Procedure B		

2.	2.0 mm/min
3.	2.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

